

CHARLES PARSONS

Technical Est. 1915

Quality: **NATURALE**

Description: Sueded polyester Oxford

Application: Print base for Flags & Banners, also suitable for table cloths, backdrops etc

Colours: Optical White

Weight: 315gsm

Width: 300cm

Roll length: 30mt/roll

Composition: 100% Polyester PFP

Coating:

Performance: Inherantly flame retardent

Natural feel and handle

76mm inner diameter core

Hot slit selvages

Manufactured from utilising eco friendly fibre

Care Insructions: Warme gentle machine wash, may be tumble dried, warm iron, drycleanable, do not bleach

The information contained in this performance specification sheet is subject to change without notice and remains the property of Charles Parsons & Co. It shall not be reproduced in whole or part, nor provided to any third parties without the written authorisation of Charles Parsons and Co. Charles Parsons Co. makes no warranty of any kind with regard to this technical specification, including but not limited to, the implied warranties of merchantability and fitness for a particular purpose. Charles Parsons Co. shall not be liable for incidental or consequential damages in connection with the supply, performance or use of this fabric. The above conditions are only a guide. A preliminary trial is recommended before using the product in production

IFLAG

NATURALE

CHARLES PARSONS

Est. 1915

LABORATORY - CERTIFIED TO AS/NZS ISO 9001:2000
TARGET ACCREDITED LABORATORY



Certified Quality Management System

FROM: Amanda Brennan
FABRIC QUALITY: FOOTBALL PLAIN
FABRIC DESC.:
DESIGN:
FIBRE CONTENT %: polyester 100
CUSTOMER:
BUYER:
SUPPLIER:

LAB REQUEST No.: **6/3617**
REQUEST DATE: 20/12/2006
PRIORITY: Normal
DEPT/STATE: Apparel Active Sydney
CONTRACT No.:
ORDER No.: MA2057624
COLOUR: WHITE (000)
END USE:
SUBMISSION TYPE: Bulk

RESULTS

Weight (g/m²)

AS2001.2.13

Width (cm)

TP22

DIMENSIONAL CHANGE

%

Washing

Normal Machine wash/Tumble dry
AS2001.5.4.2B-E(60°C)

Length

-0.8

Width

0

Pressing

160 °C

Length

-0.4

Width

-1.6

COLOURFASTNESS

Washing

AS2001.4.15 Test L1 (60 °C)

-Staining

-Cotton

-

-Nylon

-

-Change in Colour

-

Rubbing

AS2001.4.3

-Dry Staining

-

-Wet Staining

-

PILLING

CP Modified ASTM D3886-2500/5000 cycles
before wash

4-5/4-5

SEAM SLIPPAGE

AS2001.2.22 Standard seam

Warp

2 mm at 120N

Weft

OTHER

SPECTRO

DelE 0.28
Listing 0.27

ACCEPTED REJECTED

Comments:

CHARLES PARSONS

DIV. MANAGER DATE (SIGN)	
Released	
Reworked	
Disposed of/Return to mill	
Care label revised	
Customer Advised	
Accepted by Customer	

SIGNED: Khin

DATE: 21/12/2006

with allowance/concession
Copy to be returned to QAM

*REASON FOR NON-CONFORMANCE
RESULTS ARE A GUIDANCE ON PERFORMANCE